



Manufacturer:
ÅngströmBond®

Product Name:
Desolite® 950-200 Optical Fiber Coating (Splicing and Recoat Coating),
UV Cure (1 kg)

Manufacturer Part Number:
COV-950-200-1KG



[Learn More](#)

▶ [Click here for more details on the Desolite® 950-200 Optical Fiber Coating \(Splicing and Recoat Coating\), UV Cure \(1 kg\)](#)

DeSolite® Optical Fiber Coatings



Product Data

DeSolite® 950-200

Product Description

DeSolite® 950-200 UV-curable splicing compound provides long-term protection of optical fiber from moisture and chemicals. Its low viscosity makes this product suitable for all automatic and manual recoat applicators. DeSolite® 950-200 is a one-component system that has been used in the industry for more than 10 years.

Product Benefits

- Low viscosity for splicing applications
- Very low water sensitivity
- Will not stick to recoater molds
- Patent-protected

Performance Characteristics

Liquid Coating	Typical Properties
Viscosity, at 25°C, mPa•s	2500
Density, 23°C, kg•m ⁻³	1080
Refractive Index, 23°C	1.500
Surface tension, 23°C, dynes•cm ⁻¹	35

Cured Coating* (Tested at <1% R.H.)	Typical Properties
Glass Transition Range (DMA*), °C -- Peak Tan δ	26

*Dynamic Mechanical Analysis (see DMA graph)

Cured Coating* (continued) (Tested at 23°C, 50% R.H.)	Typical Properties
Secant modulus, 2.5% strain, MPa	28
Elongation, %	55
Tensile strength, MPa	9
Degree of Cure (UV dose at 95% of Ultimate Secant Modulus, J•cm ⁻²)	0.8
Cure speed by FT-IR, sec -- Time to reach 90% cure	3
Dynamic water sensitivity (250 µm films) -- weight change, % -- extractables, %	0.5 1.0
Refractive Index	1.550
Linear shrinkage on cure, %	2
Hydrogen generation (24 hrs, 80°C in air, 75 µm films, µl•g ⁻¹)	1.3
Coefficient of expansion (TMA), 500 µm films -- in glassy region (x10 ⁻⁶), °C ⁻¹ -- in rubbery region (x10 ⁻⁶), °C ⁻¹	90 250
% Transmission, 75µm film -- 1310 nm -- 1550 nm	99 99
Coefficient of friction (cured in nitro- gen): coating to stainless steel, gm • force	0.3
Adhesion to glass, per 25mm -- Dry, 50% RH, N x (10 ⁻²) -- Wet, 95% RH, N x (10 ⁻²)	14 7
Aging after 8 weeks Thermal weight change, %, -- at 125°C -- at 85°C -- at 85°C/85% RH	6 4 3

中国大陆代理商

深圳市谱兆通讯设备有限公司

Tel:+86-755-8665-5448;+86-755-8665-5579; Email:info@pztest.com Website:www.pztest.com



Manufacturer:
ÅngströmBond®

Product Name:
Desolite® 950-200 Optical Fiber Coating (Splicing and Recoat Coating),
UV Cure (1 kg)

Manufacturer Part Number:
COV-950-200-1KG



[Learn More](#)

▶ [Click here for more details on the Desolite® 950-200 Optical Fiber Coating \(Splicing and Recoat Coating\), UV Cure \(1 kg\)](#)

DeSolite® 950-200



Test Methods

Detailed test methods may be obtained through your Covestro sales representative.

Filtration

DeSolite® Optical Fiber Coatings are manufactured using fine filtration techniques designed to minimize particulate matter and to ensure high strength and uniform product performance.

Storage Conditions

Protect DeSolite® coatings from all sources of ultraviolet light, including sunlight and fluorescent light, to prevent premature curing. It is recommended that DeSolite® coatings be stored in a dry place in unopened, undamaged, original containers at temperatures between 15°C and 30°C. Storage or shipment in cold conditions may result in a phase separation which is reversible and is corrected by heating for 24 hours at 50°C. If possible, the container should be gently rolled to assure uniform dissolution during this heating process.

Shelf Life

DeSolite® 950-200 has a recommended shelf life of 2 years from the date of manufacture, provided that the above stated storage conditions are properly maintained.

Safety Information

This product is formulated with multifunctional acrylates which may cause skin and eye irritation and/or skin sensitization. Safety data sheets for each product are also available from your Fiber Optic Center sales representative. All safety and handling recommendations should be followed carefully.

Conversions

$N = g \cdot f \times 9.807 \times 10^{-3} \quad \text{kg} \cdot \text{mm}^{-2} = \text{MPa} \times 0.102$
 $\text{psi} = \text{MPa} \times 145 \quad \text{mPa} \cdot \text{s} = \text{cps}$

ÅngströmBond® is a registered trademark of Fiber Optic Center, Inc., New Bedford MA, USA

Fiber Optic Center™, Inc. MAKES NO EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS OR OTHERWISE, with respect to its products. In addition, while the information herein is believed to be reliable, no warranty is expressed or implied regarding the accuracy of the data or the results to be obtained from the use thereof. All recommendations or suggestion for use are made without guarantee – inasmuch as conditions of use are beyond our control. The properties given are typical values, and are not intended for use in preparing specifications. Users should make their own test to determine the suitability of this product for their own purposes. This warranty is limited to a credit or replacement of the product only, and does not cover direct, indirect, consequential, incidental or any other type of damage resulting from the use of the product. Fiber Optic Center is not liable for any failure to observe the precautionary measures described in this SDS or for any misuse of the product.

UPDATED 30-March-2025

中国大陆代理商

深圳市谱兆通讯设备有限公司

Tel: +86-755-8665-5448; +86-755-8665-5579; Email: info@pztest.com Website: www.pztest.com



Manufacturer:
ÅngströmBond®

Product Name:
Desolite® 950-200 Optical Fiber Coating (Splicing and Recoat Coating),
UV Cure (1 kg)

Manufacturer Part Number:
COV-950-200-1KG




[Learn More](#)

▶ [Click here for more details on the Desolite® 950-200 Optical Fiber Coating \(Splicing and Recoat Coating\), UV Cure \(1 kg\)](#)


DeSolite® 950-200



Dynamic Mechanical Analysis (DMA)



Viscosity vs. Temperature



中国大陆代理商

深圳市谱兆通讯设备有限公司

Tel: +86-755-8665-5448; +86-755-8665-5579; Email: info@pztest.com Website: www.pztest.com



Manufacturer:
ÅngströmBond®

Product Name:
Desolite® 950-200 Optical Fiber Coating (Splicing and Recoat Coating),
UV Cure (1 kg)

Manufacturer Part Number:
COV-950-200-1KG




[Learn More](#)

▶ [Click here for more details on the Desolite® 950-200 Optical Fiber Coating \(Splicing and Recoat Coating\), UV Cure \(1 kg\)](#)

DeSolite® 950-200



Cure Speed



中国大陆代理商

深圳市谱兆通讯设备有限公司

Tel: +86-755-8665-5448; +86-755-8665-5579; Email: info@pztest.com Website: www.pztest.com