



Manufacturer: ÅngströmBond®

Product Name:

ÅngströmBond® AB9093 Rigid, Low Viscosity Adhesive, UV Cure (3cc Syringe)

Manufacturer Part Number:

AB9093-3CC

Click here for more details on the AngströmBond® AB9093 Rigid, Low Viscosity Adhesive, UV Cure (3cc Syringe)



Adhesives

Advanced Polymers for High Tech Applications

ÄngströmBond® AB9093 Rigid, low viscoisty, UV adhesive

Description:

ÄngsтröмBond[®] AB9093 is a semi-rigid, low viscosity, optical adhesive designed for low stress strength bonds to glass, ceramic, metals and most plastics. This 100% solids acrylate is excellent for moisture protection and temperature cycling applications

Typical Properties:

Color:	Clear
Specific Gravity	1.1
Viscosity @ 25°C, cps:	150
Hardness, Shore D:	60
Elongation at Failure, %	16-20

Tensile Strength, psi	200
Coeff. of Exp., .ppm /°C	60
Operating Temperature, °C:	-55 to 125
Solids content, %	100
Modulus of Elasticity, psi	1500-1600
Refractive Index	1.56
Optical transmission 400-2000nm,	10um >98%

Handling Characteristics:

Cure time:

100-300 mW/cm² - 5-30 sec- . @320-390nm

Cure schedules can vary slightly with different applications.. Speed of cure depends upon thickness and light intensity. Please use these numbers as a basis to develop a schedule suitable for the application.

Storage and Shelf Life:

Store in a cool, dark place when not in use.. Do not place in view of UV light source or sunlight. Material may polymerize upon exposure to ambient light.

 $ilde{ t A}$ ngströmt Bond $ilde{ t B}$ is a registered trademark of Fiber Optic Center, Inc., New Bedford MA, USA

Fiber Optic CenterTM, Inc. MAKES NO EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS OR OTHERWISE, with respect to its products. In addition, while the information herein is believed to be reliable, no warranty is expressed or implied regarding the accuracy of the data or the results to be obtained from the use thereof. All recommendations or suggestion for use are made without guarantee — inasmuch as conditions of use are beyond our control. The properties given are typical values, and are not intended for use in preparing specifications. Users should make their own test to determine the suitability of this product for their own purposes.

Distrubutor in China: