

[Learn More](#)**Manufacturer:**
ÅngströmBond®**Product Name:**
Cablelite® 950-706 Optical Fiber Coating (Matrix Coating), UV Cure (1 kg)**Manufacturer Part Number:**
COV-950-706-1KG[Click here for more details on the Cablelite® 950-706 Optical Fiber Coating \(Matrix Coating\), UV Cure \(1 kg\)](#)

Product Data



Cablelite® 950-706

Product Description

Cablelite® 950-706 matrix material is a proven product in producing optical fiber ribbons. The versatility of this material for various ribbon designs is unsurpassed. Cablelite® 950-706 is the industry standard for optical fiber ribboning.

Product Benefits

- Extremely fast cure
- Very low water sensitivity
- Excellent low-temperature performance
- Patent protected

Performance Characteristics

Liquid Coating	Typical Properties
Viscosity, 25°C, mPa·s	4850
Density, 23°C, kg·m ⁻³	1120

Cured Coating* (Tested at <1% R.H.)	Typical Properties
Glass Transition Range (DMA**), °C at E' _{1000 MPa}	35
Glass Transition Range (DMA**), °C at E' _{100 MPa}	59

Performance Characteristics (cont'd)

Cured Coating* (Tested at 23°C, 50% R.H.)	Typical Properties
Secant modulus***, 2.5% strain, MPa -- on polyester	906
Elongation***, % -- on polyester	25
Tensile strength***, MPa -- on polyester	35
Degree of Cure (UV dose at 95% of Ultimate Secant Modulus, J·cm ⁻²)	0.3
Water Absorption after 24 hrs., 250 µm films, %	2.0
Hydrogen generation (24 hrs, 80°C in air, 75 µm films, µl·g ⁻¹)	0.2

*75 µm films cured in nitrogen at 1.0 J·cm⁻² using one D lamp, unless stated otherwise. UV dose determined with an IL-390 radiometer manufactured by International Light, Inc.

**Dynamic Mechanical Analysis (see DMA graph)

***TEM properties on polyester were obtained after 1 to 2 hours conditioning at 22 +/-2°C and 50% +/-5 RH.

中国大陆代理商

深圳市谱兆通讯设备有限公司

Tel:+86-755-8665-5448;+86-755-8665-5579; Email:info@pztest.com Website:www.pztest.com

[Learn More](#)

Manufacturer:
ÅngströmBond®

Product Name:
Cablelite® 950-706 Optical Fiber Coating (Matrix Coating), UV Cure (1 kg)

Manufacturer Part Number:
COV-950-706-1KG

▶ [Click here for more details on the Cablelite® 950-706 Optical Fiber Coating \(Matrix Coating\), UV Cure \(1 kg\)](#)

Cablelite® 950-706



Test Methods

Detailed test methods may be obtained through your Covestro sales representative.

Filtration

Cablelite® Inks and Matrix Materials are manufactured using fine filtration techniques designed to minimize particulate matter and to ensure high strength and uniform product performance.

Storage Conditions

Cablelite® matrix materials should be stored in their original containers at temperatures between 15° and 30°C. The bottles that are used for these are UV opaque and allow for air to diffuse through the plastic which prevents premature gelation.

Shelf Life

Cablelite® matrix materials have a shelf life of 18 months from the date of manufacture, provided recommended storage conditions are properly maintained.

Safety Information

This product is formulated with multifunctional acrylates which may cause skin and eye irritation and/or skin sensitization. Safety data sheets for each product are available from Fiber Optic Center sales representative. All safety and handling recommendations should be followed carefully.

Conversions

$N = g \cdot f \times 9.807 \times 10^{-3} \quad \text{kg} \cdot \text{mm}^{-2} = \text{MPa} \times 0.102$
 $\text{psi} = \text{MPa} \times 145 \quad \text{mPa} \cdot \text{s} = \text{cps}$

ÅngströmBond® is a registered trademark of Fiber Optic Center, Inc., New Bedford MA, USA

Fiber Optic Center™, Inc. MAKES NO EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS OR OTHERWISE, with respect to its products. In addition, while the information herein is believed to be reliable, no warranty is expressed or implied regarding the accuracy of the data or the results to be obtained from the use thereof. All recommendations or suggestion for use are made without guarantee – inasmuch as conditions of use are beyond our control. The properties given are typical values, and are not intended for use in preparing specifications. Users should make their own test to determine the suitability of this product for their own purposes. This warranty is limited to a credit or replacement of the product only, and does not cover direct, indirect, consequential, incidental or any other type of damage resulting from the use of the product. Fiber Optic Center is not liable for any failure to observe the precautionary measures described in this SDS or for any misuse of the product.

UPDATED 30-March-2025

中国大陆代理商

深圳市谱兆通讯设备有限公司

Tel: +86-755-8665-5448; +86-755-8665-5579; Email: info@pztest.com Website: www.pztest.com



Manufacturer:
ÅngströmBond®

Product Name:
Cablelite® 950-706 Optical Fiber Coating (Matrix Coating), UV Cure (1 kg)

Manufacturer Part Number:
COV-950-706-1KG




[Learn More](#)

▶ [Click here for more details on the Cablelite® 950-706 Optical Fiber Coating \(Matrix Coating\), UV Cure \(1 kg\)](#)


Cablelite® 950-706



Dynamic Mechanical Analysis (DMA)



Viscosity vs. Temperature



中国大陆代理商

深圳市谱兆通讯设备有限公司

Tel:+86-755-8665-5448;+86-755-8665-5579; Email:info@pztest.com Website:www.pztest.com



Manufacturer:
ÅngströmBond®

Product Name:
Cablelite® 950-706 Optical Fiber Coating (Matrix Coating), UV Cure (1 kg)

Manufacturer Part Number:
COV-950-706-1KG




[Learn More](#)

▶ [Click here for more details on the Cablelite® 950-706 Optical Fiber Coating \(Matrix Coating\), UV Cure \(1 kg\)](#)


Cablelite® 950-706



Cure Speed



Accelerated Aging



中国大陆代理商

深圳市谱兆通讯设备有限公司

Tel: +86-755-8665-5448; +86-755-8665-5579; Email: info@pztest.com Website: www.pztest.com